以微乳液法制备的锰源合成LiMn204

Synthesis Spinel $\operatorname{LiMn}_2\mathbf{0}_4$ with Manganese Carbonate Prepared by Microemulsion Method

摘要点击: 53 全文下载: 69

查看全文 查看/发表评论 下载PDF阅读器

中文关键词: 锂离子电池; Li Mn₂0₄; 融盐法

英文关键词: lithium-ion battery; Li Mn_2O_4 ; microemulsion method

基金项目:

作者 单位

杜柯 中南大学冶金科学与工程学院轻金属与工业电化学研究所,长沙 410083

其鲁 北京大学化学与分子工程学院应用化学系,北京 100080

胡国荣 中南大学冶金科学与工程学院轻金属与工业电化学研究所,长沙 410083 彭忠东 中南大学冶金科学与工程学院轻金属与工业电化学研究所,长沙 410083

中文摘要:

采用CTAB-C₈H₁₈-C₄H₉0H-H₂0微乳体系制备出MnCO₃,将其灼烧成Mn₂O₃之后,与Li $_2$ CO₃混合,800 ℃高温焙烧,获得了颗粒大小为数百纳米,均匀分布的纯相尖晶石Li Mn $_2$ O₄。这一材料的电化学性能优秀,0.5C的电流在3~4.2 V之间充放电时,首次放电比容量为124 mAh· $_2$ G⁻¹,经过110次循环,保留比容量118 mAh· $_2$ G⁻¹,平均每次容量损失<0.05%。该材料的倍率性能尤为优异,10C放电的比容量在110 mAh· $_2$ G⁻¹以上,功率约为0.2C时功率的45倍。

英文摘要:

Micro-spherical type of MnCO $_3$ was synthesized in CTAB-C $_8$ H $_1$ 8-C $_4$ H $_9$ 0H-H $_2$ 0 microemulsion system. The MnCO $_3$ was then decomposed to Mn $_2$ O $_3$ and mixed with Li $_2$ CO $_3$ and sintered at 800 °C for several hours to obtain the pure spinel LiMn $_2$ O $_4$. The LiMn $_2$ O $_4$ had initial discharge specific capacity of 124 mAh· g^{-1} at 0.5C discharge current between 3 V and 4.2 V, and kept 118 mAh· g^{-1} after 110 cycles, the loss ratio was lower than 0.05%. This material showed wonderful rate performance with cycle specific capacity of 110 mAh· g^{-1} at 10C current and the power was 45 times of that at 0.2C.

<u>关闭</u>

您是第149248位访问者

主办单位:中国化学会 单位地址:南京大学化学楼

本系统由北京勤云科技发展有限公司设计