



疏水介孔二氧化硅膜的制备与表征

Preparation and Characterization of Hydrophobic Mesoporous Silica Membranes

摘要点击: 37 全文下载: 207

[查看全文](#) [查看/发表评论](#) [下载PDF阅读器](#)

中文关键词: [介孔氧化硅薄膜](#) [孔结构](#) [疏水性](#)

英文关键词: [mesoporous silica membrane](#) [pore structure](#) [hydrophobic property](#)

基金项目:

作者

于春晓 北京工业大学材料科学与工程学院, 北京 100022
韦奇 北京工业大学材料科学与工程学院, 北京 100022
王艳丽 北京工业大学材料科学与工程学院, 北京 100022
李群艳 北京工业大学材料科学与工程学院, 北京 100022
聂祚仁 北京工业大学材料科学与工程学院, 北京 100022
邹景霞 北京工业大学材料科学与工程学院, 北京 100022

中文摘要:

用甲基三乙氧基硅烷(MTES)代替部分正硅酸乙酯(TEOS)作为前驱体, 以聚乙烯醚-聚丙烯醚-聚乙烯醚三嵌段共聚物(P123)作有机模板剂, 通过共水解缩聚反应制备了甲基修饰的介孔 SiO_2 膜。利用 N_2 吸附、FTIR、 ^{29}Si MAS NMR以及接触角测量仪对膜的孔结构和疏水性进行了表征。结果表明, 修饰后的膜材料具有良好的介孔结构, 最可几孔径为4.65 nm, 孔体积为0.69 cm³·g⁻¹, 比表面积为938.4 m²·g⁻¹; 同时疏水性明显提高, 当 $n_{\text{MTES}}/n_{\text{TEOS}}$ 达到1.0时, 其对水的接触角达到 $109^\circ \pm 1.1^\circ$ 。气体渗透实验表明气体通过膜孔的扩散由努森机制所控制。

英文摘要:

Methyl-modified mesoporous silica membranes were prepared by acid catalyzed co-hydrolysis and condensation reaction of tetraethylorthosilicate (TEOS) and methyl triethoxysilane (MTES) in the presence of triblock copolymer poly(ethylene glycol)-B-poly(propylene glycol)-B-poly(ethylene glycol) (P123) in ethanol. The pore structure and hydrophobic property of the final materials were characterized by Nitrogen adsorption, FTIR, ^{29}Si MAS NMR and contact angle meter. The results show that modified silica membranes have a desirable pore structure, with a pore size of 4.65 nm, a pore volume of 0.69 cm³·g⁻¹ and a BET surface area of 938.4 m²·g⁻¹, and tend to be hydrophobic with a water contact angle of $109^\circ \pm 1.1^\circ$, as the molar ratio of MTES/TEOS increases to 1.0. Gas permeability test suggests that the gas transport into the membranes is governed by Knudsen diffusion mechanism.

您是第594187位访问者

主办单位: 中国化学会 单位地址: 南京大学化学楼

服务热线: (025)83592307 传真: (025)83592307 邮编: 210093 Email: wjhx@netra.nju.edu.cn

[本系统由北京勤云科技发展有限公司设计](#)