

[1]王天放,李疏芬.新型高能聚合物GAP的热分解和燃烧[J].火炸药学报,2005,(1):5-08.

[点击复制](#)

新型高能聚合物GAP的热分解和燃烧



分享到:

《火炸药学报》[ISSN:1007-7812/CN:61-1310/TJ] 卷: 期数: 2005年第1期 页码: 5-08 栏目: 出版日期: 2005-03-30

Title: -

文章编号: 1007-7812(2005)01-0005-04

作者: 王天放; 李疏芬

Author(s): -

关键词: 聚合物; 推进剂黏合剂; GAP; 热分解; 燃烧性能

Keywords: -

分类号: -

DOI: -

文献标志码: -

摘要: 简要回顾了GAP的研究历程及应用情况,介绍了有关GAP的特点及研究现状,着重阐述了GAP热分解及燃烧过程的特点,给出了目前比较先进的实验方法及手段,如色谱·质谱联用、热解质谱、分子束质谱、红外激光、紫外激光、CO₂激光诱导热解等,可供进一步研究GAP参考。

Abstract: -

参考文献/References:

- [1]龚士杰. GAP推进剂综述[J]. 推进技术, 1991, (1):67-74.
- [2]张海燕, 陈红. 降低推进剂特征信号的新材料—文化GAP[J]. 火炸药学报, 1996, (3):46-48.
- [3]Golrier M. New energetic molecules and their applications in energetic materials [A]. The Proceedings of 29th ICT[C], 1998.
- [4]Calabro M. Large SRBS for future launchers [R]. AIAA. 1997.
- [5]Farber M, Harris S P, Srivastava R D. Mass spectrometric kinetic studies on several azido polymers[J]. Combust. Flame, 1984, (55):203-211.
- [6]Haas Y, Ben-Eliahu Y, Welner S. Welner infrared laser induced decomposition of GAP[J]. Combust. Flame, 1994, (96): 201-211.
- [7]Tang C J, Lee Y J, Litzinger T A. Simultaneous temperature and species measurements of the glycidyl azide polymer (GAP) propellant during laser-induced decomposition [J]. Combust. Flame, 1999, (117):244-256.
- [8]Ling P, Wight C A, Laser J. Photodissociation and thermal pyrolysis of energetic polymers [J]. Phys. Chem. B, 1997, 101(12): 2126-2131.
- [9]Takeo Saito, Masataka Shimoda, Tsuyoshi Tsuyuki, et al. CO₂ laser-induced pulsating regression behavior of GAP at sub-atmospheric pressures [J]. Combust. Flame, 2001, (124): 611-623.
- [10]Hatice Fazlioglu, Jale Hacaloglu. Thermal decomposition of glycidyl azide polymer by direct insertion probe mass spectrometry[J]. Journal of Analytical and

导航/NAVIGATE

本期目录/Table of Contents

下一篇/Next Article

上一篇/Previous Article

工具/TOOLS

引用本文的文章/References

下载 PDF/Download PDF(207KB)

立即打印本文/Print Now

导出

统计/STATISTICS

摘要浏览/Viewed

全文下载/Downloads 900

评论/Comments 625



XML

[11]陈智群, 刘艳, 刘子如, 等. GAP热分解动力学和机理研究[J]. 固体火箭技术, 2003, 26 (4) :52-54.

[12]Ger M D. Study on thermal decomposition of mixtures containing energetic binder and nitramine[J]. Thermochemical Acta, 1993, (224): 127-140.

[13]Shen Shin-ming. Thermal decomposition of cured GAP-AP propellants containing catocene [J]. Thermochemical Acta, 1993, (216): 255-265.

[14]陈沛, 赵凤起, 杨栋, 等. 纳米级金属粉对GAP热分解特性的影响[J]. 推进技术, 2000, 21 (5): 73-76.

[15]朱慧, 张炜, 王春华, 等. GAP贫氧推进剂组分的常压热分解特性研究[J]. 火炸药学报, 2001, 24 (1): 57-59.

[16]王天放, 李疏芬. 最小自由能法计算GAP的燃烧产物[J]. 火炸药学报, 2003, 26 (4): 16-19.

[17]Kubota N, Sonobe T. Combustion mechanism of azide polymer [J]. Propellants, Explosives, Pyrotechnics, 1988, (13): 172-177.

[18]Korobeinichev O P, Kuibida L V, Volkov E N. Mass spectrometric study of combustion and thermal decomposition of GAP[J]. Combust. Flame, 2002, (129) :136-150.

收稿日期: 2004年7月4日

相似文献/References:

[1]刘云飞,杨荣杰,谭惠民.固体推进剂中填料的聚合物包覆[J].火炸药学报,1997,(4):45.

Liu Yunfei, Yang Rongjie, Tan Huimin. Polymeric-based Cover of the Filler in Solid Propellants[J], 1997,(1):45.

备注/Memo: -