首页 | 简介 | 编委会 | 投稿须知 | 数据库收录

锂离子电池用 ${\rm Li}_4{\rm Ti}_5{\rm O}_{12}$ -碳复合材料的制备与电化学性能 Preparation and Electrochemical Properties of ${\rm Li}_4{\rm Ti}_5{\rm O}_{12}$ -C Composite as Anode for Lithium Ion Batteries

摘要点击: 21 全文下载: 10

查看全文 查看/发表评论 下载PDF阅读器

中文关键词: 锂离子电池; Li₄Ti₅O₁₂; 负极; 溶胶-凝胶法

英文关键词: lithium ion batteries; $\operatorname{Li}_4\operatorname{Ti}_5\operatorname{O}_{12}$; anode; $\operatorname{sol-gel}$ method

基金项目:

作者 单位

何则强 吉首大学化学化工学院,吉首 416000;中南大学化学化工学院,长沙 410083

刘文萍 吉首大学化学化工学院, 吉首 416000 熊利芝 吉首大学化学化工学院, 吉首 416000 陈上 吉首大学化学化工学院, 吉首 416000 吴显明 吉首大学化学化工学院, 吉首 416000 樊绍兵 吉首大学化学化工学院, 吉首 416000

中文摘要:

英文摘要:

 ${\rm Li}_4{\rm Ti}_5{\rm O}_{12}$ -C composite was prepared by sol-gel method using ethyl alcohol as solvent, lithium acetate and tetrabutyl titanate as raw materials, and graphite as carbon source. ${\rm Li}_4{\rm Ti}_5{\rm O}_{12}$ -C composites were characterized by thermogravimertric (TG) analysis and differential thermal analysis(DTA), X-ray diffraction(XRD), Fourier transform infrared (FTIR) spectroscopy, scanning electron microscopy (SEM) and electrochemical tests. Results show that ${\rm Li}_4{\rm Ti}_5{\rm O}_{12}$ -C composite with 5% carbon containing can be obtained by annealing the precursor at 600 °C for 6 h in ${\rm N}_2$ atomsphere. The composites can deliver a specific capacity of 167.1 mAh· ${\rm g}^{-1}$, 99.0% and 105.1% of the capacity can be retained after discharged for 80 times at 0.1C and 2.0C, respectively. Compared with pure ${\rm Li}_4{\rm Ti}_5{\rm O}_{12}$ -C composite shares larger discharge capacity, better cyclability and rate performance.

关闭

您是第149249位访问者

主办单位:中国化学会 单位地址:南京大学化学楼

本系统由北京勤云科技发展有限公司设计