



航空学报 » 1999, Vol. 20 » Issue (4) :48-51 DOI:

论文

[最新目录](#) | [下期目录](#) | [过刊浏览](#) | [高级检索](#)

[<<](#) [<<](#) [前一篇](#) | [后一篇](#) [>>](#) [>>](#)

TiAl合金PST晶体中Ti₃Al片层取向对其蠕变性能的影响

林建国, 张永刚, 陈昌麒

北京航空航天大学材料科学与工程系

EFFECT OF Ti₃Al LAMELLAR ORIENTATION ON THE CREEP BEHAVIOR OF TiAl PST CRYSTAL

LIN Jian guo, ZHANG Yong gang, CHEN Chang qi

Department of Materials Science and Engineering, Beijing University of Aeronautics and Astronautics, Beijing, 100083, China

摘要

参考文献

相关文章

Download: [PDF \(266KB\)](#) [HTML](#) OKB Export: [BibTeX](#) or [EndNote \(RIS\)](#) [Supporting Info](#)

摘要 对2种硬取向(φ=90°和0°, φ为外力轴与片层界面的夹角)的TiAl合金PST晶体试样的高温压缩性能及蠕变性能进行了测试,并对其蠕变组织进行了观察。结果表明:2种取向试样的屈服强度及蠕变性能存在明显的差异;在T=800℃,σ=350MPa蠕变条件下,φ=90°试样过早出现蠕变失稳阶段,这与该取向试样片层组织中α₂相在蠕变过程中发生球化及剪切带的形成有关。

关键词:

Abstract: The yield strength and creep curves of TiAl PST crystals with two 'hard' orientations (i.e., φ=90° and 0°, φ is the angle between loading axis and lamellar boundaries) at high temperature have been measured and compared, and the deformation structures of the crept samples have been examined by using SEM and TEM. The results indicated that the yield strength and creep behavior were quite different between these two oriented samples; Under the condition of T=800℃ and σ=350MPa, the earlier onset of tertiary creep was found in the sample with φ=90°, which may be caused by the spheroidization of α₂ phase and the formation of shear band during creep.

Keywords:

Received 1998-07-01;

引用本文:

林建国;张永刚;陈昌麒. TiAl合金PST晶体中Ti₃Al片层取向对其蠕变性能的影响[J]. 航空学报, 1999, 20(4): 48-51.

LIN Jian guo;ZHANG Yong gang;CHEN Chang qi . EFFECT OF Ti₃Al LAMELLAR ORIENTATION ON THE CREEP BEHAVIOR OF TiAl PST CRYSTAL[J]. Acta Aeronautica et Astronautica Sinica, 1999, 20(4): 48-51.

Service

- ▶ 把本文推荐给朋友
- ▶ 加入我的书架
- ▶ 加入引用管理器
- ▶ Email Alert
- ▶ RSS

作者相关文章