

Effect of Mica and Glass on Acrylic Teeth Material's Color

Idil DIKBAS¹, Temel KOKSAL¹, Fatma UNALAN², Ozlem GURBUZ³, Fuat NOYUN¹ and Ender KAZAZOGLU¹

¹Department of Prosthodontics, Faculty of Dentistry, Yeditepe University, Istanbul, Turkey

²Department of Prosthodontics, Faculty of Dentistry, Istanbul University, Istanbul, Turkey

³Department of Dentistry, Bakırkoy Mental Hospital, Istanbul, Turkey

Corresponding author, Idil Dikbas E-mail: idildikbas@yeditepe.edu.tr

Received February 22, 2006/Accepted April 6, 2006

The purpose of this study was to evaluate the effect of two different ratios of silanized mica filler and milled glass fiber reinforcement on the color of acrylic denture teeth materials. Ten acrylic resin discs made of acrylic denture teeth material (PMMA) obtained from the manufacturer were used as the control group. Four experimental groups were modified from the control group's PMMA material by adding a ratio of 5% or 10% by weight of silane-treated mica filler or milled glass fibers. Each group consisted of 10 specimens. Measurements were performed using a spectrophotometer CM-2600d, and the color changes were characterized in the Commission Internationale d'Eclairage L*a*b* color space. ΔE^* values of 5% mica-, 10% mica-, 5% glass-, and 10% glass-containing sample groups were 2.46, 3.03, 2.16, and 2.59 respectively. There were statistically significant differences in L*, a*, and b* values between the control group and each test group. It was shown that when PMMA denture teeth material was modified with silane-treated mica filler or silane-treated milled glass fibers for the purpose of reinforcement, it would also cause significant changes to the original color of the material.

Key words : Color, Spectrophotometer, Acrylic denture teeth

INTRODUCTION

Acrylic resin teeth, which have been widely used in prosthetic dentistry, have some advantages over porcelain teeth. Acrylic denture teeth made of polymethyl methacrylate (PMMA) have excellent fracture toughness, allow easy occlusal adjustment, and demonstrate high bond strength with denture base materials. However, their wear resistance poses a problem^{1–3}. To overcome this problem, different types of material have been added to polymer materials to improve their mechanical properties and wear resistance^{1,4} — namely carbon fibers⁵, aramid fibers⁶, glass fibers^{7–9}, and mica fillers^{10,11}.

Inorganic fillers in PMMA are subjected to silane coupling treatment to enhance the adhesion of these particles to the matrix base of the teeth material^{12–15}. Unalan *et al.*¹¹ found that addition of silanized mica in the ratios of 5% and 10% significantly decreased the wear rates of PMMA. Likewise, Gurbuz *et al.*⁹ observed that addition of similar ratios of glass fibers caused the wear rates of PMMA to decrease significantly. However, reinforcement additives might change the original color of denture teeth material (PMMA). The purpose of this study, therefore, was to evaluate the effect of two different ratios of silanized mica filler and milled glass fibers on the color of acrylic denture teeth materials.

MATERIALS AND METHODS

Test materials

Denture teeth material, PMMA (Ruthinium Dental Manufacturing, Italy), was supplied in the lightest shade in both powder and liquid forms. Acrylic resin discs made of PMMA were prepared according to the manufacturer's instructions. These specimens were used as the control group. Four experimental groups were modified from the control group's PMMA material by adding two different ratios (5%, 10%) of silane-treated mica filler and two different ratios (5%, 10%) of silane-treated milled glass fibers by weight. As a result, one control and four experimental groups were obtained (Table 1). Each group consisted of 10 samples. The dimensions of each sample were 16 mm in diameter and 7 mm in thickness.

For the silane-treated muscovite mica filler (DYO Boya Fabrikalari Sanayii ve Ticaret A.Ş., İzmir, Turkey) used in this study, its physical prop-

Table 1 Contents of control group and test groups

| Group | Content |
|---------------|----------------------------|
| Control group | PMMA |
| Test group 1 | 5% mica filler-added PMMA |
| Test group 2 | 10% mica filler-added PMMA |
| Test group 3 | 5% glass fiber-added PMMA |
| Test group 4 | 10% glass fiber-added PMMA |

PMMA: Polymethyl methacrylate

erties were: *ca.* 32 μm in particle size, 2.7 g/cm^3 in density, and 2.5 in Mohs hardness. As for the silane-treated milled E glass fibers (Cam Elyaf A.Ş., Çayırova, Turkey), the physical properties were: 32 μm in particle size, 1.2 μm in diameter, 0.8 mm in length, 2.54 g/cm^3 in density, and 6.5 in Mohs hardness. The silane coupling agent, A-174 (which contained 3-methacryloxypropyl trimethoxy silane, 3-MPS), was supplied from Union Carbide, UK.

Specimen preparation

Control group specimens were prepared in 20 g/10 ml powder/liquid (P/L) ratio according to the manufacturer's recommendations. To incorporate mica into PMMA material, the P/L ratio was decreased to 20 g/14 ml. This modified P/L ratio was used to ensure better impregnation of the mica filler. For the impregnation of glass fibers, it was not necessary to change the control group's P/L ratio. To obtain mixtures containing 5% and 10% ratios of silane-treated mica filler and silane-treated glass fibers by weight, required weights of these additives were predetermined.

Initially, the control group was prepared according to the predetermined P/L ratio. Then, the required additive amount of each test group was added to the predetermined weight of PMMA powder and mixed thoroughly. Following which, the required volume of PMMA liquid was added to the mixture and stirred so that the additives were randomly oriented to give isotropic properties to the composite. The flaked acrylic resin dough was polymerized at 175 $^{\circ}\text{C}$ under a pressure of 160 bar for three minutes (Elimko 2200 Hydrocontrol Machine, Ankara, Turkey) and then cooled with water under a pressure of 160 bar for three minutes. After demoulding, specimen surfaces which were to be used for color measurements had a glossy texture. These specimens were stored in distilled water at $37 \pm 1^{\circ}\text{C}$ in a closed, dark box until evaluation.

Color change measurement

After removal from the distilled water, the color of each group's specimens was measured by a spectrophotometer, CM 2600-d (Konica Minolta Sensing, Inc., Japan).

Before measurement, the colorimeter was calibrated according to the manufacturer's instructions by using the supplied white calibration standard. Measurements were taken at three different points of each sample. The mean value of these three measurements was automatically calculated by the spectrophotometer and recorded.

Color changes were characterized in the Commission Internationale d'Eclairage $L^*a^*b^*$ color space (CIE $L^*a^*b^*$). The CIE $L^*a^*b^*$ system was employed in this study because it is well suited for the determination of small color differences¹⁶⁾. Direction

of a color difference is described by the magnitude and algebraic sign of each component — ΔL^* , Δa^* , and Δb^* — as follows:

$$\Delta L^* = L_{\text{test}} - L_{\text{control}}, \quad \Delta a^* = a_{\text{test}} - a_{\text{control}}, \\ \text{and } \Delta b^* = b_{\text{test}} - b_{\text{control}}$$

where L_{control} , a_{control} , and b_{control} refer to the color values of the control samples, while L_{test} , a_{test} , and b_{test} refer to the color values of the test samples. All the samples of the four experimental groups were randomly matched to the control group's specimens, and each test group's samples had their respective ΔL^* , Δa^* , and Δb^* values.

For each of these components — ΔL^* , Δa^* , and Δb^* , their signs bear the following approximate meanings: + ΔL^* = lighter, — ΔL^* = darker, + Δa^* = redder (less green), — Δa^* = greener (less red), + Δb^* = yellow (less blue), and — Δb^* = bluer (less yellow)¹⁷⁾. As for the color difference between the control and test samples, it was expressed as a single parameter, ΔE^* , which was calculated from the following formula^{5,18)}:

$$\Delta E^* = [(\Delta L)^2 + (\Delta a)^2 + (\Delta b)^2]^{1/2}$$

To relate the amount of color change (ΔE^*) recorded by the spectrophotometer to a clinical environment, the data were converted to National Bureau of Standards units (NBS units) through the following equation:

$$\text{NBS units} = \Delta E^* \times 0.92$$

where critical remarks of color differences as expressed by NBS units are shown in Table 2¹⁹⁾.

Statistical analysis

Color change between control and each test group was statistically analyzed using Mann-Whitney U test. Mean ΔL^* , Δa^* , and Δb^* values of test groups were compared by Kruskal-Wallis test at the 95% confidence level.

RESULTS

Color values of the control and test groups are shown in Table 3. Table 4 shows the differences between the control and each test group in L^* , a^* , and b^* values (*i.e.*, ΔL^* , Δa^* , and Δb^* respectively), as well as the ΔE^* value of each test group. As shown

Table 2 National Bureau Standards (NBS) ratings

| NBS unit | Critical remarks of color differences |
|--------------|---------------------------------------|
| 0.0–0.5 | Trace: Extremely slight change |
| 0.5–1.5 | Slight: Slight change |
| 1.5–3.0 | Noticeable: Perceivable change |
| 3.0–6.0 | Appreciable: Marked change |
| 6.0–12.0 | Much: Extremely marked change |
| 12.0 or more | Very much: Change to other color |

in Table 4, there were no significant differences among the test groups' values ($p > 0.05$).

Table 5 shows the color difference value (ΔE^*) and its corresponding NBS value for all test groups. According to this table, the NBS ratings of all test groups were within the range of 1.5-3.0, which meant that a noticeable color change was observed. In other words, test samples containing 5% mica, 10%

mica, 5% glass, and 10% glass showed noticeable color differences when compared to the control group samples.

Table 6 shows the dual comparison results between each test group and control group. In each test group, L^* , a^* , and b^* values were significantly different from the control group's corresponding values ($p < 0.05$).

Table 3 Color values of the control and four test groups

| | | L^* | a^* | b^* |
|--------------------------|------|-------|-------|-------|
| Control | Mean | 69.27 | 0.45 | 11.76 |
| | SD | 0.73 | 0.19 | 0.41 |
| Test group 1 (5% mica) | Mean | 67.12 | 0.99 | 12.53 |
| | SD | 0.51 | 0.11 | 0.56 |
| Test group 2 (10% mica) | Mean | 66.64 | 1.19 | 12.80 |
| | SD | 0.98 | 0.34 | 0.30 |
| Test group 3 (5% glass) | Mean | 67.29 | 0.88 | 12.24 |
| | SD | 0.64 | 0.17 | 0.39 |
| Test group 4 (10% glass) | Mean | 67.10 | 0.96 | 12.90 |
| | SD | 0.55 | 0.14 | 0.29 |

SD: Standard deviation

Table 4 Differences between control and each test group in L^* , a^* , and b^* values, as well as the ΔE^* value of each test group and Kruskal-Wallis results

| | | Group 1 (5% mica) | Group 2 (10% mica) | Group 3 (5% glass) | Group 4 (10% glass) | KW | P |
|--------------|------|----------------------|-----------------------|-----------------------|------------------------|------|-------|
| ΔL^* | Mean | -2.15 | -2.62 | -1.98 | -2.17 | 1.51 | 0.678 |
| | SD | 0.72 | 1.16 | 0.68 | 0.79 | | |
| Δa^* | Mean | 0.54 | 0.73 | 0.42 | 0.51 | 4.55 | 0.216 |
| | SD | 0.22 | 0.40 | 0.27 | 0.21 | | |
| Δb^* | Mean | 0.77 | 1.04 | 0.48 | 1.14 | 7.73 | 0.052 |
| | SD | 0.62 | 0.48 | 0.48 | 0.48 | | |
| ΔE^* | Mean | 2.46 | 3.03 | 2.16 | 2.59 | 5.20 | 0.157 |
| | SD | 0.56 | 0.98 | 0.62 | 0.66 | | |

$P > 0.05$: Insignificant

SD: Standard deviation

KW: Kruskal-Wallis statistical test

Table 5 Color changes of test groups

| | ΔE^* | NBS unit | Remark of color difference |
|--------------------------|--------------|----------|----------------------------|
| Test group 1 (5% mica) | 2.46 | 2.26 | Noticeable |
| Test group 2 (10% mica) | 3.03 | 2.78 | Noticeable |
| Test group 3 (5% glass) | 2.16 | 1.99 | Noticeable |
| Test group 4 (10% glass) | 2.59 | 2.38 | Noticeable |

NBS: National Bureau of Standards

Table 6 Dual comparison of each test group to control group

| | L* | a* | b* |
|-----------|--------------|-------------|--------------|
| | Mean (SD) | Mean (SD) | Mean (SD) |
| Control | 69.27 (0.73) | 0.45 (0.19) | 11.76 (0.41) |
| 5% mica | 67.12 (0.51) | 0.99 (0.11) | 12.53 (0.56) |
| MW | 0 | 0 | 13 |
| P | 0.0001 | 0.0001 | 0.005 |
| Control | 69.27 (0.73) | 0.45 (0.19) | 11.76 (0.41) |
| 10% mica | 66.64 (0.98) | 1.19 (0.34) | 12.80 (0.30) |
| MW | 0 | 0 | 1 |
| P | 0.0001 | 0.0001 | 0.0001 |
| Control | 69.27 (0.73) | 0.45 (0.19) | 11.76 (0.41) |
| 5% glass | 67.29 (0.64) | 0.88 (0.17) | 12.24 (0.39) |
| MW | 3 | 4 | 20 |
| P | 0.0001 | 0.001 | 0.023 |
| Control | 69.27 (0.73) | 0.45 (0.19) | 11.76 (0.41) |
| 10% glass | 67.10 (0.55) | 0.96 (0.14) | 12.90 (0.29) |
| MW | 0 | 1 | 1 |
| P | 0.0001 | 0.0001 | 0.0001 |

SD: Standard deviation

MW: Mann-Whitney U statistical test

DISCUSSION

Color changes can be evaluated visually as well as by instrumental techniques. Since instrumental measurements eliminate the subjective errors in visual color comparison, spectrophotometers were used instead of the Munsell color order system for visual evaluation²⁰.

The CIE* L*a*b* color order system provides a useful tool for quantifying the color properties of dental materials. Color is described using a mathematical three-dimensional system based on an equal distance in the color space that is directly correlated with equal perceived gradations. This system divides color into three attributes. L* is a measure of whiteness or brightness. a* measures the hue-chroma in the red-green direction, while b* measures hue-chroma in the yellow-blue axis. High L* values are obtained for bright or white samples. Positive a* values are red, negative values are green. Positive b* values are yellow, negative values are blue²¹.

Color difference (ΔE^*) was calculated from the formula previously mentioned. However, there are various approaches to assessing the ΔE^* value. It has been reported by Seghi *et al.*²² that a ΔE^* value equal to 1 was considered visually detectable in 50% of the cases, whereas a ΔE^* value greater than 2 was detectable in all cases. Um and Ruyter²⁰ also suggested that a ΔE^* value equal to 1 was "visually perceptible". Similarly, Liberman *et al.*²³ concluded that a value of $\Delta E^*=1$ should be sufficient to discriminate between color stability and perceptible

change.

On the other hand, in a study performed by Yannikakis *et al.*²⁴, a ΔE^* value ≤ 2 was considered "visually imperceptible", whereas a ΔE^* value greater than 2 was used as a baseline and stated as "visually perceptible". Similarly, Stober *et al.* claimed that only color differences with ΔE^* ranging from 2 to 3 were visible²⁵. On the same note, Ikeda *et al.*²⁶ stated that ΔE^* values between 0 and 2 were imperceptible, values between 2 and 3 were just perceptible, values between 3 and 8 were moderately perceptible, and values above 8 were markedly perceptible. A color change that is more than perceptible (*i.e.*, $\Delta E^* > 1.0$)²⁰ will be considered as acceptable up to the value of $\Delta E^*=3.3$, which is considered to be the upper limit of acceptability in subjective visual evaluations²⁷. Indeed, Ruyter *et al.*²⁷ described discolorations of $\Delta E^* > 3.3$ as no longer clinically acceptable. In a study by Yannikakis *et al.*²⁴, it was shown that for two similar looking – but different – samples based on a porcelain shade guide, the color difference was found to be 1.85 units.

Although ΔE^* values are accepted as measures of color change, it is difficult to equate these numeric values and the accompanying degree of color change to a clinical setting and the perception of color change by an observer. One method frequently used to determine the degree of color difference and thus a practical application of ΔE^* color notation is to convert it to National Bureau of Standards (NBS) units. NBS critical remarks of color differences are

used for color comparison and quality control functions, because only the ΔE^* value needs specification rather than a range of L^* , a^* , and b^* values. However, with these values, it is possible to determine color changes that occur in test materials¹⁹.

In the present study, the authors preferred to determine the differences in L^* , a^* , and b^* values between the control group and each test group. Following which, ΔE^* values which showed substantial color differences were also calculated. In addition, corresponding NBS units were calculated to assess clinical acceptability.

As seen in Tables 3 and 4, changes in L^* value of all test groups were toward the negative direction, which meant that addition of both mica and glass resulted in loss of brightness. When the mean L^* value of the control group was compared to the mean L^* value of each test group, maximum difference was observed with the 10% mica-containing group ($\Delta L^* = -2.62 \pm 1.16$) while minimum difference was seen in the 5% glass-containing group ($\Delta L^* = 1.98 \pm 0.68$). Similar results were obtained with the Δa^* value. The 5% glass-containing group yielded the lowest difference ($\Delta a^* = 0.42 \pm 0.27$) while the 10% mica-containing group yielded the highest difference ($\Delta a^* = 0.73 \pm 0.40$). On the overall, the a^* values of all test groups changed towards redness. In the b^* chromaticity coordinate, the highest change was in the 10% glass-containing group ($\Delta b^* = 0.14 \pm 0.48$).

It meant that this group showed a change that was yellower. In summary, there were statistically significant differences in the L^* , a^* , and b^* values between the control group and each test group.

ΔE^* values of 5% mica-, 10% mica-, 5% glass-, and 10% glass-containing groups were 2.46, 3.03, 2.16, and 2.59 respectively. Some authors^{20,28,29} assumed that values of $\Delta E^* < 1$ were regarded as not appreciable by the human eye. Values of $1 < \Delta E^* < 3.3$ were regarded as appreciable by skilled operators, but considered clinically acceptable. However, values of $\Delta E^* > 3.3$ were considered appreciable even by non-skilled persons, and for that reason considered as clinically unacceptable^{20,28,29}. Therefore, ΔE^* values found in this study were supposed to be clinically acceptable. At this juncture, it must be highlighted that this result is valid for discolorations originating from staining agents. But for reinforcement materials added to denture teeth material (such as PMMA), it is desirable that the original color of PMMA be preserved. In this study, although the color differences were clinically acceptable, the L^* values of all test groups changed towards the darker side — which meant that the lightest shade of PMMA was lost.

When the results were evaluated in terms of NBS units of color difference, the 10% mica-containing test group exhibited the greatest chromatic change (2.78). The lowest chromatic change belonged to the

5% glass-containing test group (1.99) (Table 5). Nonetheless, according to NBS ratings (Table 2), the color difference of all test groups was considered noticeable (*i.e.*, perceivable change). In other words, this clinical remark also indicated that the original shade of PMMA had changed. Therefore, it should be noted that if denture teeth were reinforced by adding mica filler or glass fibers, then even the denture teeth material of the lightest shade on the shade scale will yield a resultant color that is darker than its original shade.

CONCLUSIONS

The effects of two reinforcement additives in two different ratios were evaluated from the perspective of the color stability of the original PMMA denture teeth material. Within the limitations of this *in vitro* study, the following conclusions were drawn:

- 1) When PMMA denture teeth material was modified by silane-treated mica filler or silane-treated milled glass fibers for the purpose of reinforcement, significant changes to the original color of the material occurred, as shown in the L^* , a^* , and b^* values.
- 2) All test groups exhibited “noticeable” color changes according to NBS critical remarks of color differences.
- 3) 10% mica-containing test group exhibited a greater chromatic change than the other test groups.
- 4) Denture teeth manufacturers are therefore encouraged to supply reinforcement materials which do not affect the selected original shade of PMMA.

REFERENCES

- 1) Craig RG. Restorative dental materials, 11th ed., Mosby, St Louis, Missouri, USA, 2002, pp.672-675.
- 2) Ekfeld A, Oilo G. Wear mechanisms of resin and porcelain teeth. Acta Odontol Scand 1989; 47: 391-399.
- 3) Anusavice KJ. Philliphs' science of dental materials, 11th ed., Saunders, St Louis, Missouri, USA, 2003, pp.754-755.
- 4) Hirano S, May KB, Wagner WC, Hacker CH. *In vitro* wear of resin denture teeth. J Prosthet Dent 1998; 79: 152-155.
- 5) Larson WR, Dixon DL, Aquilino SA, Clancy JMS. The effect of carbon graphite fiber reinforcement on the strength of provisional crowns and fixed partial denture resins. J Prosthet Dent 1991; 66: 816-820.
- 6) Berrong JM, Weed Rw, Young JM. Fracture resistance of Kevlar-reinforced poly(methyl methacrylate) resin: A preliminary study. Int J Prosthodont 1990; 3: 391-395.
- 7) Vallittu PK, Lassila VP. Reinforcement of acrylic denture base material with metal or fibre strengtheners. J Oral Rehabil 1992; 19: 225-230.
- 8) Solnit GS. The effect of methyl methacrylate reinforcement with silane-treated and untreated glass fibers. J Prosthet Dent 1991; 66: 310-314.

- 9) Gurbuz O, Unalan F, Kursoglu P. *In vitro* wear of denture teeth acrylic resin with milled glass fiber composite. *Oral Health and Dental Management in the Black Sea Countries* 2005; 4: 46-51.
- 10) Sen S, Nugay N. Tuning of final performance of unsaturated polyester composites with inorganic microsphere/platelet hybrid reinforces. *European Polymer Journal* 2001; 37: 2047-2053.
- 11) Unalan F, Gurbuz O, Nilhan N, Bilgin P, Sermet B. Effect of mica as filler on wear of denture teeth polymethylmethacrylate (PMMA) resin. *Balk J Stom* (in press).
- 12) Debnath S, Ranade R, Wunder SL, McCool J, Boberick K, Baran G. Interface effects on mechanical properties of particle-reinforced composites. *Dent Mater* 2004; 20: 67-88.
- 13) Halvorson RH, Erickson RL, Davidson CL. The effect of filler and silane content on conversion of resin-based composite. *Dent Mater* 2003; 19: 327-333.
- 14) Lim BS, Ferracane JL, Condon JR, Adey JD. Effect of filler fraction and filler surface treatment on wear of microfilled composites. *Dent Mater* 2002; 18: 1-11.
- 15) Zhao FM, Takeda N. Effect of interfacial adhesion and statistical fiber strength on tensile strength of unidirectional glass fiber/epoxy composites. Part I: Experiment results. *Dent Mater* 2000; 31: 1203-1214.
- 16) Khokhar ZA, Razzoog ME, Yaman P. Color stability of restorative resins. *Quintessence Int* 1991; 22: 733-737.
- 17) Belli S, Tanriverdi FF, Belli E. Colour stability of three esthetic laminate materials against to different staining agents. *J Marm Un Dent Fac* 1997; 2: 643-648.
- 18) Rosentritt M, Esch J, Behr M, Leibrock A, Handel G. *In vivo* color stability of resin composite veneers and acrylic resin teeth in removable partial dentures. *Quintessence Int* 1998; 29: 517-522.
- 19) Razzoog ME, Lang BR, Russell MM, May KB. A comparison of the color stability of conventional and titanium dental porcelain. *J Prosthet Dent* 1994; 72: 453-456.
- 20) Um CM, Ruyter IE. Staining of resin-based veneering materials with coffee and tea. *Quintessence Int* 1991; 22: 377-386.
- 21) Vargas MA, Kirchner HL, Diaz-Arnold AM, Beck VL. Color stability of ionomer and resin composite restoratives. *Oper Dent* 2001; 26: 166-171.
- 22) Seghi RR, Hewlett ER, Kim J. Visual and instrumental colorimetric assessments of small color differences on translucent dental porcelain. *J Dent Res* 1989; 68: 1760-1764.
- 23) Liberman R, Combe EC, Piddock V, Watts DC. Color changes in acrylic teeth-comparison of an objective and subjective method. *J Oral Rehabil* 1996; 23: 464-469.
- 24) Yannikakis SA, Zissis AJ, Polyzois GL, Caroni C. Color stability of provisional resin restorative materials. *J Prosthet Dent* 1998; 80: 533-539.
- 25) Stober T, Gilde H, Lenz P. Color stability of highly filled composite resin materials for facings. *Dent Mater* 2001; 17: 87-94.
- 26) Ikeda T, Nakanishi A, Yamamoto T, Sano H. Color differences and color changes in Vita shade tooth-colored restorative materials. *Am J Dent* 2003; 16: 381-384.
- 27) Ruyter IE, Nilner K, Moller B. Color stability of dental composite resin materials for crown and bridge veneers. *Dental Mater* 1987; 3: 246-251.
- 28) Inokoshi S, Burrow MF, Kataumi M, Yamada T, Takatsu T. Opacity and color changes of tooth-colored restorative materials. *Oper Dent* 1996; 21: 73-80.
- 29) Kim HS, Um CM. Color differences between resin composites and shade guides. *Quintessence Int* 1996; 27: 559-567.